

PRODUCT DATA HARD HAT® AEROSOLS STRIPING PAINT 2300

DESCRIPTION

RUST-OLEUM® Hard Hat Aerosol Striping Paint 2300 is based on a fast drying short oil alkyd. The products are based on lead- and chromate free pigments.

RECOMMENDED USES

RUST-OLEUM Striping Paint 2300 should be used in light traffic exposure.
RUST-OLEUM Striping Paint 2300 is designed for use together with the Rust-Oleum Striping Machine.
RUST-OLEUM Striping Paint 2300 is ideal for drawing lines in parking areas, plants, warehouses, sports fields, stadiums and all sites where traffic control is required.

TECHNICAL DATA

Appearance: Flat
Colour: See colour card
Propellant: Dimethyl ether
VOC-content: 625 g/l

Drying times 20°C/50% r.v.
To touch: 20 minutes
To handle: 4 hours
To recoat: Within 1 hour or after 48 hours
Full hardness 7 days

Heat resistance: 100°C (dry heat)

Coverage

Theoretical: 60 metres at a width of 10 cm.
Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove dirt, grease, oil and all other surface contaminants by appropriate means. The surface must be clean and dry during application.

DIRECTION FOR USE

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Turn can upside down and place into can-holder of the Rust-Oleum Striping Machine. See that spray head is properly placed into opening; the elongated part of the spray button should be parallel to the wheel axle. The can-holder is adjustable. When the holder is in its lowest position a line of approx. 5 cm wide can be drawn. When the holder is in the highest position the width of the line is approx. 10 cm. Intermediate widths can be obtained by varying the position of the holder. Pull trigger handle to activate the spraying. Striping machine should be moving whilst spraying to prevent inside build up of coating material.
After use turn can upright and press spray button for 2 - 3 seconds to clean valve.

APPLICATION CONDITIONS

For good results the relative humidity shall be below 85% and the temperature of the can and substrate above 0°C.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@rustoleumdirect.co.uk
www.rustoleumdirect.co.uk

PRODUCT DATA HARD HAT® AEROSOLS STRIPING PAINT 2300

SHELLIFE / STORAGE CONDITIONS

3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Andrews Coatings Ltd
Carver Building
Littles Lane
Wolverhampton
West Midlands
WV1 1JY

Tel. 01902 429190

info@rustoleumdirect.co.uk
www.rustoleumdirect.co.uk